

roof reviver

**Breathes new life
into tired roofs**

Gloss 100% Acrylic Roof Rehabilitation and Protective Coating

Description

The Roof Reviver system is specifically designed using premium acrylic binders and pigmentation to give the highest level of resistance to Australian weather conditions. Roof Reviver restores not only the aesthetics of the roof but also its integrity and inhibits the growth of mould and lichen.

Roof Reviver system comprises:

- Tilewash
- Primerlock
- Roof Reviver

Tilewash

Remove all dirt, moss, lichen, mould and all other surface contaminants using medium pressure water blasting (min. 3000 P.S.I.) taking care not to damage pointing or tiles. Apply Tilewash to the roof using a suitable brush, roller or garden sprayer ensuring complete wetting to kill remaining spores; after approximately 1 hour (preferably overnight) wash roof thoroughly with clean water. Ensure surface is clean, dry and defect-free before proceeding.

Primerlock

Apply one coat of Primerlock to achieve a single wet coat, to enable the coating to seal the surface. It is important to seal the entire tile placing particular attention to the nose of the tile.

Roof Reviver

Apply 2 coats of Roof Reviver to the sealed concrete roof tile, ensuring uniform coating to flat and nose of tile. Allow a minimum of 2 hours between coats (allow longer in cold weather). Do not apply in windy conditions to avoid overspray

Application of Primerlock and Roof Reviver should not be carried out when the surface temperature is outside the range of 10 to 30 degrees Celsius. In very hot weather it is recommended that a light spray of clean water is applied to cool the roof and assist penetration and adhesion.


Concrete Roof Tile Coating System			
	Dry Film Thickness	Theoretical Spreading rate	Recoat
Pre-treatment High pressure wash with clean water to remove all dirt and plant growth.			
Tilewash Apply Tilewash with low pressure hand spray to achieve a full saturation. Allow 1 hour minimum (or overnight) to kill all spores and wash thoroughly with clean water.			Allow roof to completely dry before proceeding
1st Coat			
Primerlock (apply by airless spray – do not apply excessively)	Min 20µm Max 25µm	12.5 m2 per litre 12.5 m2 per litre	2 Hours
2nd Coat			
Roof Reviver Topcoat (apply by airless spray)	Min 50µm Max 100µm	10 m2 per litre 5.0 m2 per litre	2 Hours Indefinite
3rd Coat			
Roof Reviver Topcoat (apply by airless spray)	Min 50µm Max 100µm	10.0 m2 per litre 5.0 m2 per litre	2 Hours Indefinite

Airless Spray Application:


Equipment should be a piston operated Airless Spray sufficiently rated to spray high build material with the equivalent of a GRACO #521 or 525 nozzle (other configurations can be used subject to the job).

Colours

Shown below are standard colours* available in Roof Reviver. Special Colours are available upon request.





Black




Charcoal



Mahogany




Brunswick Green




Sandy Beach



Ochre



Storm Grey




Heritage Red




Slate Grey




Cooper Pedy



Wafer



Dove Grey



Cabernet